

Flexfoam Gun 888

General purpose, gun applied polyurethane foam



Description

Flexfoam Gun 888 is one component, self-expanding, high yield polyurethane foam which can be applied using a polyurethane foam applicator gun.

Flexfoam Gun 888 is developed to react with the humidity to give excellent thermal and sound insulation properties with strong adhesion to common construction substrates.

Applications

Flexfoam Gun 888 can be used for:

- ▲ Filling and sealing of gaps, joints, cavities and penetrations.
- ▲ Mounting and sealing of window and door frames.
- ▲ Thermal insulation of wall panels and roof stones.
- ▲ Insulating electrical outlets and pipes.

Advantages

- ▲ Excellent adhesion to most common building substrates.
- ▲ Gun applied giving the advantage of reusability.
- ▲ High thermal and acoustical insulation.
- ▲ Extended filling capacities.
- ▲ Can be over painted when cured.

Limitations

- ▲ Sensitive to UV and direct sun light.
- ▲ Not recommended for use in contact with Teflon, polyethylene and silicon surfaces.

Method of Use

Surface Preparation

Surfaces must be sound, clean, and free of oil and grease. Spray small amounts of water onto the substrate prior to the application. For cold applications, Flexfoam Gun 888 must be kept in a warm room where the temperature does not exceed 30°C before the application.

Application

Shake Flexfoam Gun 888 well before using then attached the aerosol can onto the applicator gun. The discharge rate can be controlled by controlling the pressure on the trigger of the gun.

Technical Properties:

Density:	25 ± 5 kg/m ³
Tack-free time:	15 ± 5 min
Cutting time: (30 mm bead)	35 ± 5 min
Curing time:	> 18 hr @ 23°C
Application temperature:	5°C to 30°C
Service temperature:	-50°C to 90°C
Volume shrinkage:	None
Compression strength: DIN 53421	3 N/cm ²
Tensile strength: BS 5241	10 N/cm ²
Thermal conductivity:	0.034 W/(m.K)
Sound reduction index:	60 dB

Fill half of the cavities' volume and leave the foam to expand in the joint, then refill as necessary. Flexfoam Gun 888 aerosol can must be kept upside down during the time of discharging.

Cleaning

Uncured foam can be cleaned using acetone. Cured material can only be removed mechanically.

Packaging

Flexfoam Gun 888 is packaged in 750 ml aerosol cans holding 888 g.

Storage

Flexfoam Gun 888 has a shelf life of 12 months from the date of manufacturing if stored in the original unopened cans at temperatures between 5°C and 30°C away from direct sunlight, snow and rain.

If these conditions are exceeded, DCP Technical Department should be contacted for advice.

Flexfoam Gun 888

Cautions

Health and Safety

Flexfoam Gun 888 contains diphenylmethane 4,4-diisocyanate. Apply in well ventilated areas. Do not smoke. Do not apply near naked flames. In closed areas use force ventilation and carbon active masks. Use protective clothing and gloves.

For further information refer to the Material Safety Data Sheet.

Fire

Flexfoam Gun 888 is flammable.

More from Don Construction Products

A wide range of construction chemical products are manufactured by DCP which include:

- ▲ Concrete admixtures.
- ▲ Surface treatments
- ▲ Grouts and anchors.
- ▲ Concrete repair.
- ▲ Flooring systems.
- ▲ Protective coatings.
- ▲ Sealants.
- ▲ Waterproofing.
- ▲ Adhesives.
- ▲ Tile adhesives and grouts.
- ▲ Building products.
- ▲ Structural strengthening.

Note:

We endeavour to ensure that any information, advice or recommendation we may give in product literature is accurate and correct. However, because we have no control over where and how products are applied, we cannot accept any liability arising from the use of the products.

